

Weaving Construction	Type	Yarn Used		Density (counts/25mm)		Width (cm)	Roll Length (m)	Thickness (mm)	Weight (g/m ²)
		Warp	Welt	Warp (inch)	Welt (inch)				
Plain	Carbon	3K	3K	12.8 (13)	12.8 (13)	100~150	100	0.25	200
2/2Twill	Carbon	3K	3K	12.8 (13)	12.8 (13)	100~150	100	0.25	200
Plain	Carbon	3K	3K	14.8 (15)	14.8 (15)	100~120	100	0.27	240
2/2Twill	Carbon	3K	3K	14.8 (15)	14.8 (15)	100~120	100	0.27	240
Plain	Carbon	12K No Twist	12K No Twist	3.27 (3.32)	3.27 (3.32)	100~120	100	0.22	210
Plain	Carbon	12K No Twist	12K No Twist	3.00 (3.05)	3.00 (3.05)	100~120	100	0.21	192
Plain	Carbon	12K	12K	5.9 (6.0)	5.9 (6.0)	100~150	100	0.43	380
2/2Twill	Carbon	12K	12K	5.9 (6.0)	5.9 (6.0)	100~150	100	0.43	380
Plain	Carbon	12K	12K	6.4 (6.5)	6.4 (6.5)	100~150	100	0.52	420
2/2Twill	Carbon	12K	12K	6.4 (6.5)	6.4 (6.5)	100~150	100	0.52	420
Plain	Carbon	12K	12K	7.4 (7.5)	7.4 (7.5)	100~150	100	0.61	480
2/2Twill	Carbon	12K	12K	7.4 (7.5)	7.4 (7.5)	100~150	100	0.61	480

